

LOCTITE® 420

December 2020

Product description

LOCTITE® 420 provides the following product characteristics:

Technology	Cyanoacrylate
Chemical type	Ethyl cyanoacrylate
Appearance (uncured)	Transparent, colorless to straw colored liquid
Components	One component – requires no mixing
Viscosity	Very low
Cure	Humidity
Application	Bonding
Key substrates	Plastics, rubbers and metals

LOCTITE® 420 is a general purpose cyanoacrylate instant adhesive.

Mil-A-46050C

LOCTITE® 420 is tested to the lot requirements of Military Specification Mil-A-46050C. **Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

Commercial Item Description A-A-3097:

LOCTITE® 420 has been qualified to commercial item description A-A-3097. **Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

Typical properties of uncured material

Specific Gravity @ 25°C	1.05
Viscosity, Cone & Plate, mPa·s (cP): Temperature: 25°C, shear rate: 3,000 s ⁻¹	1 to 4
Viscosity, brookfield - LVF, 25°C, mPa·s (cP): Spindle 1, speed 6 rpm	1 to 5
Vapour pressure, hPa	<1
Flash point - see SDS	

Typical curing performance

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22 °C / 50% relative humidity. This is defined as the time to develop a shear strength of 0.1 N/mm².

Fixture Time, seconds:


Mild steel (degreased)	10 to 30
Aluminum (degreased)	5 to 15
Zinc dichromate	30 to 90
Neoprene	<5
Rubber, nitrile	<5
ABS	10 to 30
PVC	3 to 10
Polycarbonate	20 to 60
Phenolic	5 to 20

Cure speed vs. bond gap

The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure.

Cure speed vs. humidity

The rate of cure will depend on the ambient relative humidity. The following graph shows the tensile strength developed with time on Buna N rubber at different levels of humidity.



Cure speed vs. activator

Where cure speed is unacceptably long due to large gaps, applying activator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect.

Typical properties of cured material

After 24 hours @ 22°C

Physical properties:

Coefficient of Thermal Expansion, ISO 11359-2, K ⁻¹ :	100×10 ⁻⁶
Coefficient of Thermal Conductivity, ISO 8302, W/(m·K)	0.1
Softening Point, DIN EN 1427, °C	165

Electrical properties:

Dielectric Constant / Dissipation Factor, IEC 60250:

0.1 kHz	2 to 3.3 / <0.02
1 kHz	2 to 3.5 / <0.02
10 kHz	2 to 3.5 / <0.02
Volume resistivity, IEC 60093, Ω·cm	2×10 ¹⁵ to 10×10 ¹⁵
Surface resistivity, IEC 60093, Ω	10×10 ¹⁵ to 80×10 ¹⁵
Dielectric Breakdown Strength, IEC 60243-1, kV/mm	25

Typical performance of cured material**Adhesive properties**

After 24 hours @ 22 °C

Lap shear strength:

Steel (grit blasted)	N/mm ²	15 to 26 (2,175 to 3,770)
Aluminum (grit blasted)	N/mm ²	12 to 19 (1,740 to 2,755)
ABS	N/mm ²	6 to 13 (870 to 1,885)
PVC	N/mm ²	6 to 20 (870 to 2,900)
Polycarbonate	N/mm ²	6 to 20 (870 to 2,900)
Phenolic	N/mm ²	5 to 20 (725 to 2,900)
Neoprene	N/mm ²	5 to 15 (725 to 2,175)
Nitrile	N/mm ²	5 to 15 (725 to 2,175)
Tensile strength, ISO 6922:		
Steel	N/mm ²	12 to 25 (1,740 to 3,625)
Buna-N	N/mm ²	5 to 15 (725 to 2,175)

"T" Peel Strength, ISO 11339:

Steel (degreased)	N/mm (lb/in)	<0.5 (<2.8)
Buna-N	N/mm ² (psi)	≥6.0 (≥870)

After 10 sec @ 22°C

Tensile strength, ISO 6922:

Buna-N	N/mm ² (psi)	≥6.0 (≥870)
--------	----------------------------	----------------

Typical environmental resistance


Cured for 1 week @ 22 °C

Lap shear strength:
Mild steel (grit blasted)**Hot strength**

Tested at temperature

Heat Aging

Aged at temperature indicated and tested @ 23 °C.

**Chemical/solvent resistance**

Aged under conditions indicated and tested @ 23 °C.

Environment	°C	100 h	500 h	1000 h
Motor oil (MIL-L-46152)	40	100	100	95
Gasoline	22	100	100	100
Isopropanol	22	100	100	100
Ethanol	22	100	100	100
Freon TA	22	100	100	100
1,1,1 Trichloroethane	22	100	100	100
Heat/humidity 95% RH	40	80	75	65
Heat/humidity 95% RH on polycarbonate	40	100	100	100



General information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet.

Directions for use

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05mm).
3. Excess adhesive can be dissolved with LOCTITE cleanup solvents, nitromethane or acetone.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product package labeling.

Optimal Storage: 2°C to 8°C. Storage below 2°C or greater than 8°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Approval and certificate

Please contact Henkel representative for related approval or certificate of this product.

Data ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.



**In case products are delivered by Henkel Colombiana, S.A.S.
the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2